

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

CODE **CG353**

TYPE

DG1/70 HS GP blue

COMPOSITION


Conveying surface	Material	Synthetic elastomer		
	Thickness	3.00	mm	0.118 in.
	Surface pattern	GP		
	Colour	Blue		
	Coefficient of friction	HF		
Textile carcass	Material	Polyamide (PA)		
	Plies no.	---		
	Weft type	---		
Driving surface	Material	Synthetic elastomer		
	Thickness	0.50	mm	0.020 in.
	Surface pattern	FL		
	Colour	Black		

TECHNICAL SPECIFICATIONS

Total thickness		6.50	mm	0.26	in.
Weight		6.00	kg/m ²	1.22	lbs./sq.ft
Elongation at 1%		5.0	N/mm	29.0	lbs./in.
Max. admissible pull		10	N/mm	57.0	lbs./in.
Temperature resistance ⁽¹⁾	min.	-20	°C	-4	°F
	max.	100	°C	212	°F
⁽¹⁾ use of the belt with limit values may reduce its life					
Minimum roller diameter ⁽²⁾					
■ Knife edge		no			
■ Bending roller		75	mm	3.0	in.
■ Counter-bending roller		100	mm	3.9	in.
⁽²⁾ The above mentioned values depend on the type of CHIORINO joint recommended					
Coefficient of friction on driving surface					
■ Raw steel sheet		0.20	[-]		
■ Laminated plastic/wood		0.25	[-]		
■ Steel roller		0.20	[-]		
■ Rubberized roller		0.30	[-]		
Max. production width		500	mm	20	in.

SUITABLE FOR

Corrugated carton: folding




FEATURES

Humidity influence	yes
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	no
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	no
Chemical resistances link	7

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

Issue: 01-07-2021

Last Update: 20-05-2024

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

CODE CG353

TYPE

DG1/70 HS GP blue

• Recommended joining procedure SKIVED JOINT '4'



Check our general catalogue to get further info on CHIORINO joining methods.


• Skiving instructions

Skiver	Belt thickness mm	Length mm	Straight/ diagonal cut	Cam/ wedge number	Pulley				Top cover			
					T mm	B mm	Thickness adjustment	End stop switch of working plate	T mm	B mm	Thickness adjustment	End stop switch of working plate
B600 A	6,5	65	Diagonal	1.5-14	---	2,5	17,6	105	---	15	13,70	115
B300 SA	6,5	65	Diagonal	1,5-14	42	2,5	11,6	---	45	15	8,7	(*)

• Guide to the use of adhesives

Apply the **K cement** on the polyamide part of the splices.
 Apply the **H primer** and then the **B cement** on the two elastomer parts of each skived end.
 Let dry for 5 minutes, then match the belt ends, paying attention to align properly.
 Press according to the instructions shown.
 To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

• Layout of components



Press settings

Upper platen temperature	120 °C
Lower platen temperature	120 °C
Curing time in press	25 min.
Driving torque	2,5
Cooling time: it is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.	

• Notes

(*) Attention: used the bloc as a limit switch for the cam. Do not overcome the bloc.

Issue: 29-06-2021

Last Update: 25-03-2022

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.