

FLAT TRANSMISSION BELTS

TECHNICAL DATA SHEET

LA	IIKANSI	VIIOOIUN	BELIS				TECHNICAL DATA SHEET
CODE CG37							LL4
0.1							
C	OMPOSITION						
	Material	Leather					
Top	Finish						
	Colour	Grey					
	Coefficient of friction	0,4					
Traction	Material	Polyamide	e (PA)				
	Material	Leather					
ace	Finish						
surface	Colour	Grey					
	Coefficient of friction	0,4					
TE	ECHNICAL SP	ECIFICATIO	NS			F	EATURES
Tota	al thickness		4.80 mm	0.19	in.	- Well	performing with severe overload applications, as they
Wei	ight		5.00 kg/m ²	1.02	lbs./sq.ft	allow	temporary sliding on pulleys without getting damaged
	mum pulley dine above mentio		150 mm pend on running sp	<i>5.9</i> ee	in.		
Pull	for 1% elonga	ation	15.0 N/mm	86	lbs./in.		
Ten	sile strength		600 N/mm	3426	lbs./in.		
Tem	nperature	min.	0 °C	32	°F		
	stance (2)	max	80 °C	176	°F		
			nay reduce its life	V/25			
	nidity influence			yes		CO	DMPLIANCES
Perr (UN	nanent antista I EN ISO 2117	itic dynamica '9)	ally	no		REACH	H EC 1907/2006 Regulation and Amendments
Botl	n sides can be	used for pov	ver transmission	yes			
SI	UITABLE FOR	l					
Рар	er industry						
Flor	ır mills					P. 1	0.150
00							OTES
							with double chrome leather covers
						Beits	for multiple or cross drives
T	uo. 07.06.3	206					Lock Hodekay 20 10 2012
155	ue: 07-06-20	סטכ					Last Update: 28-10-2013

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



FLAT TRANSMISSION BELTS

JOINING DATA SHEET

LL4 **CG37** CODE **TYPE** SKIVED JOINT '3' · Recommended joining procedure Check our general catalogue to get further info on CHIORINO joining methods.

· Skiving instructions

Skiver	Belt thickness	Length	Straight/ Cam/ wedge number		Pulley				Top cover			
	mm	mm		Т	В	Thickness adjustment	End stop switch of working	Т	В	Thickness adjustment	End stop switch of working plate	
					mm	mm		plate mm	mm	mm		plate
B600 A	5.1	95	Straight	2-10					59	15	16,00	
B300 SA	5.1	95	Straight	2-10					62	15	09-15	

· Guide to the use of adhesives


Pour the I hardener with the R cement (pot life 2 hours), then apply a thin layer of this mix on the leather area of the splice, lightly tapping with the brush. Wait until it dries.

Spread the **K cement** on the polyamide area of the skive and allow it to dry for 5 minutes.

Spread again the R+I mix on the leather area, again in a thin layer and let it dry for 5 minutes, then match the belt ends, checking their perfect alignment.

Press according to the instructions shown. To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

· Layout of components



Press settings					
Upper platen temperature	90 °C				
Lower platen temperature	90 °C				
Curing time in press	20 min.				
Driving torque	30				
Cooling time:					

ti is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.

Notes

Issue: 10-12-2005 Last Update: 30-01-2014

DISCLAIMERThe information

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees "C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.