

FLAT TRANSMISSION BELTS

TECHNICAL DATA SHEET

		MISSICIA					TECHNICAL DATA SHEET		
CC	DDE CG	38			т	YPE	LL6		
0	OMBOSITION								
C	OMPOSITION								
	Material	Leather							
Top surface	Finish								
	Colour	Grey							
	Coefficient of friction	0,4				Ш			
Traction core	Material	Polyamide	(PA)						
Bottom surface	Material	Leather							
	Finish								
Bott	Colour	Grey							
	Coefficient of friction	0,4							
TE	ECHNICAL SP	ECIFICATIO	NS				FEATURES		
Total thickness 6.00 mm 0.24 in.			in.	- Well performing with severe overload applications, as t allow temporary sliding on pulleys without getting damage					
Wei	ight		6.00 kg/m ²	1.22	lbs./sq.ft	alli	ow temporary snumg on puneys without getting damaged		
	imum pulley di ne above mentio		200 mm pend on running sp	<i>7.9</i> ee	in.				
Pull	for 1% elonga	ation	20.0 N/mm	114	lbs./in.				
Ten	sile strength		800 N/mm	4568	lbs./in.				
Tem	mperature min. 0 °C 32 °F								
	stance (2)	max	80 °C nay reduce its life	176	°F				
	nidity influence		lay reduce its ille	yes					
			llv				COMPLIANCES		
(UN	manent antista II EN ISO 2117	'9)		no		RE	ACH EC 1907/2006 Regulation and Amendments		
Botl	h sides can be	used for pow	er transmission	yes					
S	UITABLE FOR	l							
Pap	er industry								
Flou	Flour mills					NOTES			
						Ве	Its with double chrome leather covers		
						Ве	lts for multiple or cross drives		
Iss	ue: 07-06-20	006				'	Last Update: 28-10-2013		

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



FLAT TRANSMISSION BELTS

JOINING DATA SHEET

LL6 **CG38** CODE **TYPE** SKIVED JOINT '3' · Recommended joining procedure Check our general catalogue to get further info on CHIORINO joining methods.

· Skiving instructions

Skiver	Belt thickness mm	Length	Straight/ diagonal cut	Cam/ wedge number	Pulley				Top cover			
					Т	В	Thickness adjustment	End stop switch of working plate	Т	В	Thickness adjustment	End stop switch of working plate
					mm	mm		piate	mm	mm		piate
B600 A	6.2	115	Straight	2-10					80	17	15,70	
B300 SA	6.2	115	Straight	2-10					83	17	09-13	

· Guide to the use of adhesives


Pour the I hardener with the R cement (pot life 2 hours), then apply a thin layer of this mix on the leather area of the splice, lightly tapping with the brush. Wait until it dries.

Spread the **K cement** on the polyamide area of the skive and allow it to dry for 5 minutes.

Spread again the R+I mix on the leather area, again in a thin layer and let it dry for 5 minutes, then match the belt ends, checking their perfect alignment.

Press according to the instructions shown. To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

· Layout of components



Press settings					
Upper platen temperature	90 °C				
Lower platen temperature	90 °C				
Curing time in press	30 min.				
Driving torque	30				

Cooling time: it is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.

Notes

Issue: 10-12-2005 Last Update: 30-01-2014

DISCLAIMER The information

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees "C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.