


PROFILES and GUIDES

TECHNICAL DATA SHEET

ES128 T40 U W CODE **TYPE**

DESCRIPTION

Polyurethane lateral profile, straight.



TECHNICAL SPECIFICATIONS

| Material Polyurethane (TPU | | | | | PU) |
|---|---------------------|---------------|----------|---------|-------|
| Hardness | | | | 85 ±5 S | Sh.A |
| Colour | | White | | | |
| Base | | | | | Flat |
| 3 Upper base | | 20.0 | mm | 0.79 | in |
| Bottom base | | | mm | | in |
| l Height | | 40.0 | mm | 1.57 | in |
| Veight | | 211 | gr/m | 0.188 | oz/in |
| 1inimum pitch | | | | | |
| longitudinal | | | mm | | in |
| transversal | | 45 | mm | 1.8 | in |
| linimum pulley diamet | ters ⁽¹⁾ | | | | |
| longitudinal-driving side | | | mm | | ir |
| longitudinal-conveying side | | | mm | | ir |
| transversal-conveying side | | 60 | mm | 2.4 | ir |
| 1) Minimum pulley diameters refer | red to environme | ent condition | ons of 2 | 0°C | |
| emperature | min. | -20 | °C | -4 | ۰F |
| resistance (2) | max | 70 | °C | 158 | ٥F |
| ²⁾ Use with limit values may reduc | e its life | | | | |
| Roll/bar sizes | | 2.4 | m | 7.9 | ft |

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments HACCP (Hazard Analysis and Critical Control Points) FDA (Food and Drug Administration)

METHOD OF APPLICATION

- High frequency welding

NOTES

Last Update: 22-01-2020 Issue: 22-01-2020

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.