


PROFILES and GUIDES

TECHNICAL DATA SHEET

ES152 S12 U CODE **TYPE**

DESCRIPTION

Profile fitted transversally or longitudinally.



TECHNICAL SPECIFICATIONS

| PU) | hane (TI | lyuret | Po | | Material |
|-------|----------|-----------|---------------|---------------------|------------------------------------|
| Sh.A | 70 ±5 S | | | | Hardness |
| een | Gr | | | | Colour |
| ved | Groo | | | | Base |
| in. | 0.47 | mm | 12.0 | | B Upper base |
| in. | | mm | | | b Bottom base |
| in. | 0.47 | mm | 12.0 | | H Height |
| oz/in | 0.120 | gr/m | 135 | | Weight |
| | | | | | Minimum pitch |
| in. | 1.8 | mm | 45 | | longitudinal |
| in. | 1.8 | mm | 45 | | ■ transversal |
| | | | | ters ⁽¹⁾ | Minimum pulley diame |
| in | 3.9 | mm | 100 | side | longitudinal-driving |
| in | 6.3 | mm | 160 | ng side | ■ longitudinal-conveyi |
| in | 3.2 | mm | 80 | ng side | ■ transversal-conveyi |
| | °C | ons of 20 | ent condition | rred to environme | (1) Minimum pulley diameters refe |
| ۰F | -4 | °C | -20 | min. | Temperature |
| ٥F | 158 | °C | 70 | max | resistance (2) |
| | | | | ce its life | (2) Use with limit values may redu |
| ft | 328.0 | m | 100.0 | | Roll/bar sizes |

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments FDA (Food and Drug Administration)

METHOD OF APPLICATION

- Hot air welding
- High frequency welding

NOTES

Last Update: 27-05-2021 Issue: 22-01-2020

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.