


SIDEWALLS

TECHNICAL DATA SHEET

C-U 20/80

DESCRIPTION

Sidewalls fitted longitudinally.



TECHNICAL SPECIFICATIONS

| TECHNICAL SPECIFICA | IIONS | | | | |
|--|------------------|--------------------|-----------|--------------------|--|
| Material | | Polyurethane (TPU) | | | |
| Colour | | | | Green | |
| Hardness | | | 8 | 85 ±5 Sh.A | |
| B = Base | | 42 | mm | 1,65 in. | |
| H = Height | | 80 | mm | 3,15 in. | |
| P = Pitch | | 50 | mm | 1,97 in. | |
| Thickness | | 1.7 | mm | 0,07 in. | |
| Weight | | 146 | gr/m | 0.130 oz/in. | |
| Minimum pulley diameter | s ⁽¹⁾ | | | | |
| longitudinal-conveying side | | 190 | mm | 7.5 in. | |
| (1) Minimum pulley diameters referred | to environme | ent condition | ons of 20 | °C | |
| Temperature | min. | -20 | °C | -4 °F | |
| resistance (2) | max | 70 | °C | 158 ∘ _F | |
| (2) Use with limit values may reduce its | s life | | | | |
| Preformed or multiple roll length | | 25.0 | m | 82.0 ft | |

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments FDA (Food and Drug Administration)

METHOD OF APPLICATION

- High frequency welding

NOTES

Issue: 22-01-2020 Last Update: 22-01-2020

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.