


PROFILES and GUIDES

TECHNICAL DATA SHEET

ES389 T30 CODE **TYPE**

DESCRIPTION

PVC lateral profile, straight.



TECHNICAL SPECIFICATIONS

| chloride (PV | yl chl | Polyvin | | Material |
|-------------------|----------|--------------|----------------------|------------------------------------|
| 60 ±5 Sh | | | | Hardness |
| Gre | | | | Colour |
| Groove | | | | Base |
| n 0.91 | mm | 23.0 | | B Upper base |
| າ | mm | | | b Bottom base |
| 1.18 | mm | 30.0 | | H Height |
| m 0.307 <i>oz</i> | gr/m | 345 | | Weight |
| | | | | Minimum pitch |
| ı | mm | | | longitudinal |
| 1 2.2 | mm | 55 | | ■ transversal |
| | | | eters ⁽¹⁾ | Minimum pulley diame |
| n | mm | | side | longitudinal-driving |
| ı | mm | | ing side | longitudinal-convey |
| n 3.2 | mm | 80 | ng side | transversal-conveyi |
| f 20°C | ns of 20 | ent conditio | erred to environm | (1) Minimum pulley diameters refe |
| 14 | °C | -10 | min. | Temperature |
| 140 | °C | 60 | max | resistance (2) |
| | | | uce its life | (2) Use with limit values may redu |
| 7.9 | m | 2.4 | | Roll/bar sizes |

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

METHOD OF APPLICATION

- High frequency welding

NOTES

Last Update: 22-01-2020 Issue: 22-01-2020

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.