

TECHNICAL DATA SHEET



CODE L	A-88		TYPE X-W 60 GP NR
COMPOSITI	ON		
Material	Natural elastomer compound	(NR)/thermoplastic	
Colour	Purple red		
Hardness	40 ± 5 Sh.A		
Outer surface pattern	GP		
Inner surface pattern	Smooth		
TECHNICAL Total thickness	. SPECIFICATIONS $5.5 \pm 0,20 \text{ mm} \qquad 0.22$	± 0.008 in.	COMPLIANCES REACH Regulation EC 1907/2006 and amendments
Weight	5.0 ± 0,20 kg/m² 1.02	± 0.008 lbs./sq.ft	SUITABLE FOR
Production widt	h 1200 mm	47 in.	Packaging
Temperature resistance (1)	min20 °C max. +80 °C	-4 °F 176 °F	Ceramic industry Wood industry
(1) use of the sheeting	ng with limit values may reduce its life		
Issue: 29-	-06-2015	Last Update 23-06-2016	

DISCLAIMERThe information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.