

SEAMLESS BELTS

TECHNICAL DATA SHEET

CODE **MN-362**

TYPE

MF R-300

BELT STRUCTURE

Outer cover

Material	Natural elastomer
Cover finish	Ground surface
Colour	Purple red
Hardness	45 \pm 5 Sh.A
Coefficient of friction	- Paper 2.0 - Plastic 2.0

Traction core

Material	Polyester (PET)
----------	-----------------

Inner cover

Material	Polyester (PET) fabric
Colour	Black
Hardness	--- \pm 5 Sh.A

TECHNICAL SPECIFICATIONS

Available range of standard thicknesses (1)	from 10.1 to 12.0 mm
	" 0.4 " 0.5 in

(1) Please contact CHIORINO S.p.A. for special requirements.

Diameter sizes	As per mandrels list
----------------	----------------------

Elongation 1%	10 N/mm 57 lbs/in
---------------	-------------------

Permanent antistatic dynamically (UNI EN 21179)	yes
---	-----


Pulley diameter	According to the total thickness
-----------------	----------------------------------

Temperature resistance (2)	min. -20 °C -4 °F max +100 °C 212 °F
----------------------------	---

(2) Use of a mandrel made belt with limit values may reduce its life.

SUITABLE FOR

Box folding industry: feeding



FEATURES

- Good resistance to alcohols and glycols
- Fair resistance to aqueous solutions of acids and alkalis, natural and synthetic oils
- Poor resistance to solvents, hydrocarbons, acids and concentrated alkalis

CHEMICAL RESISTANCES

Class: 8 (See chart of chemical resistances)

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

Suitable for abrasive smooth cardboard, PVC boxes, corrugated cardboard.

No joint: manufactured with endless technology which guarantees endless uniformity of the surface and the coefficient of friction.

Issue: 10-07-2008

Last Update: 28-10-2013

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.