


## PT1.2 U2-U5

### COMPOSITION

Conveying surface	Material	Polyurethane (TPU)		
	Thickness	0.5	mm	0.020 in.
	Surface pattern	Matt		
	Colour	Green		
	Coefficient of friction	HF		
Textile carcass	Material	Polyester (PET)		
	Plies no.	1		
	Weft type	Rigid		
Driving surface	Material			
	Thickness	0.2	mm	0.008 in.
	Surface pattern	Matt		
	Colour	Black		



### TECHNICAL SPECIFICATIONS

Total thickness	1.20 mm	0.05 in.
Weight	1.30 kg/m <sup>2</sup>	0.27 lbs./sq.ft
Elongation at 1%	5 N/mm	29.0 lbs./in.
Max. admissible pull	5 N/mm	28.6 lbs./in.
Temperature resistance <sup>(1)</sup>	min.	-20 °C
	max.	+100 °C

<sup>(1)</sup> Use of the belt with limit values may reduce its life.

Minimum roller diameter <sup>(2)</sup>		
■ Knife edge	no	
■ Bending roller	20 mm	0.8 in.
■ Counter-bending roller	25 mm	1.0 in.

<sup>(2)</sup> The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface		
■ Raw steel sheet	0.40 [-]	
■ Laminated plastic/wood	0.50 [-]	
■ Steel roller	0.40 [-]	
■ Rubberized roller	0.60 [-]	

Max. production width	2000 mm	79 in.
-----------------------	---------	--------

### SUITABLE FOR

Paper industry: cutters  
Printing and graphic: wrapping / binding

### FEATURES

Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	no
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	no
Chemical resistances <a href="#">link</a>	5

### COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments  
FDA (Food and Drug Administration)

### NOTES

PRODUCT CODE NA1029

Last Update: 03-05-2024

#### DISCLAIMER


The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

### PT1.2 U2-U5

#### Recommended joining procedure

MICRO Z - 30 x 6 mm

Other joining methods can be used:



A = 30 mm  
B = 6 mm


Check our general catalogue to get further info on CHIORINO joining methods.

#### • Pressing

##### Heating press P \ PL \ PLS

Press settings	
Upper platen temperature	160 °C
Lower platen temperature	160 °C
Temperature gauge setting	160 °C
Curing time in press	3 min.
Pressure	3 bar
Film	none
Cement	---


1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.

3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

#### • Layout of components



#### • Notes

PRODUCT CODE NA1029

Last Update: 30-01-2014


#### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

## PT1.2 U2-U5

**• Recommended jointing procedure**
**“FAST JOINT” MICRO Z**

Other jointing methods can be used:



A = 30 mm  
B = 6 mm


Check our general catalogue to get further info on CHIORINO jointing methods.

**• Pressing**
**Heating press P120 FJ**


Press settings	
Upper platen temperature	200 °C
Lower platen temperature	200 °C
Temperature gauge setting	200 °C
Curing time in press	4 min.
Cooling time	10 min.

**Advice for the press adjustment:**

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.
3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

**• Layout of components**

**• Notes**

Tighten spring until close-wound.

PRODUCT CODE NA1029

Last Update: 28-01-2020

**DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.