

## **CONVEYOR AND PROCESS BELTS**

#### **TECHNICAL DATA SHEET**

# 2M12 U0-V5 FR

	CMDOCITIO	N.			
COMPOSITION					
Conveying surface	Material	PVC 70 Sh.A (±5)			
	Thickness	0.50	mm	0.020	in.
	Surface pattern	Smooth			
Con	Colour	Black			
	Coefficient of friction	LF			
e S	Material	Polyester (PET)			
<b>Textile</b> carcass	Plies no.	2			
⊢ წ	Weft type	Rigid			
	Material	Fabric with polyurethane (TPU) impregnation			
<b>Driving</b> surface	Thickness		mm		in.
	Surface pattern	LdB fab	ric		
	Colour	Grey			

TECHNICAL SPECI	FICATIO	NS		
Total thickness		2.20 mm	0.09	in.
Weight		$2.40 \text{ kg/m}^2$	0.49	lbs./sq.ft
Elongation at 1%		12 N/mm	69.0	lbs./in.
Max. admissible pull		24 N/mm	137.0	lbs./in.
Temperature resistance (1)	min.	-10 °C	14	°F
resistance (1)	max.	60 °C	140	°F
(1) Use of the belt with limit va	lues may re	duce its life.		

Minimum radius / diameter (2)		
Knife edge minimum radius	no	
■ Bending roller min. diameter	50 mm	1.97 in.
<ul><li>Counter-bending roller min. diameter</li></ul>	60 mm	2.36 in.
(2) The above mentioned values depend on the type of CHIORINO joint recommended.		

# Coefficient of friction on driving surface

	J	
Raw steel sheet	0.20 [-]	
Laminated plastic/wood	0.25 [-]	
■ Steel roller	0.20 [-]	
Rubberized roller	0.30 [-]	
Max. production width	2000 mm	79 in.

## **SUITABLE FOR**

Airports

Airports: check-in Materials handling



FEATURES	
Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	no
Chemical resistances link	9

Last Update: 23-06-2016

### **COMPLIANCES**

REACH EC 1907/2006 Regulation and Amendments Flame Retardant UNI EN ISO 340 Flame Retardant UL94HB Horizontal Burning

**NOTES** 

PRODUCT CODE NA1070

## DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




#### **CONVEYOR AND PROCESS BELTS**

#### JOINING TECHNICAL DATA SHEET

# 2M12 U0-V5 FR

## Recommended joining procedure

#### SINGLE Z - 80 x 10 mm



#### Other joining methods can be used:

DIAGONAL SINGLE Z DOUBLE Z SKIVED JOINT '1'


Check our general catalogue to get further info on CHIORINO joining methods.

#### Pressing

#### P\PL\PLS **Heating press**


Press settings	
Upper platen temperature	175 °C
Lower platen temperature	175 °C
Temperature gauge setting	175 °C
Curing time in press	3 min.
Pressure	3 bar
Film	TC673 - Film PVC FR
Cement	

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- 3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

## · Layout of components



#### Notes

#### Last Update: 17-04-2024 PRODUCT CODE NA1070

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.