

2M8 U0-U-G15 HS FL

COMPOSITION

Conveying surface	Material	Synthetic elastomer			
	Thickness	1.50	mm	0.059 in.	
	Surface pattern	FL			
	Colour	Green			
	Coefficient of friction	MF			
Textile carcass	Material	Polyester (PET)			
	Plies no.	2			
	Weft type	Rigid			
Driving surface	Material	Fabric with polyurethane (TPU) impregnation			
	Thickness	---	mm	---	in.
	Surface pattern	Fabric			
	Colour	Black			

TECHNICAL SPECIFICATIONS

Total thickness	3.00 mm	0.12 in.
Weight	3.40 kg/m ²	0.69 lbs./sq.ft
Elongation at 1%	8 N/mm	46.0 lbs./in.
Max. admissible pull	16 N/mm	91.4 lbs./in.
Temperature resistance ⁽¹⁾	min. -20 °C max. 100 °C	-4 °F 212 °F

⁽¹⁾ Use of the belt with limit values may reduce its life.

Minimum radius / diameter ⁽²⁾

■ Knife edge minimum radius	no
■ Bending roller min. diameter	50 mm 1.97 in.
■ Counter-bending roller min. diameter	70 mm 2.76 in.

⁽²⁾ The above mentioned values depend on the type of CHIORINO joint recommended.


Coefficient of friction on driving surface

■ Raw steel sheet	0.20 [-]
■ Laminated plastic/wood	0.25 [-]
■ Steel roller	0.20 [-]
■ Rubberized roller	0.30 [-]

Max. production width	1800 mm	71 in.
-----------------------	---------	--------

SUITABLE FOR

Corrugated carton: feeder
Printing and graphic: insertion cassettes wind./unwinding
Wood industry
Packaging
Airports
Mechanical industry




FEATURES

Humidity influence	no
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	yes
Inclined conveying	
Accumulators belts	no
Curved conveyor	no
Chemical resistances link	6

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

PRODUCT CODE NA1134

Last Update: 01-03-2019


DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

2M8 U0-U-G15 HS FL

Recommended joining procedure

DOUBLE Z



Other joining methods can be used:

SKIVED JOINT '2'


Check our general catalogue to get further info on CHIORINO joining methods.

• Pressing

Heating press P \ PL \ PLS

Press settings	
Upper platen temperature	180 °C
Lower platen temperature	110 °C
Temperature gauge setting	145 °C
Curing time in press	2 min.
Pressure	2 bar
Film	TC33 - Transparent PU film
Cement	---


1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.

3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

• Layout of components



• Notes

PRODUCT CODE NA1134

Last Update: 30-01-2014

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.