

TYPE

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

2T12 U0-U-G10 HS FH

CODE NA1135

Conveying

Material Synthetic elastomer Thickness 1.00 mm 0.039 in. Surface pattern Colour Green Coefficient of friction Material Polyester (PET) Plies no. 2 Weft type Flexible	COMPOSITION											
Surface pattern Colour Green Coefficient of friction Material Polyester (PET) Plies no. 2		Material	Synthetic elastomer									
Coefficient of friction Material Polyester (PET) Plies no. 2	a)		1.00 mm <i>0.039 in.</i>									
Coefficient of friction Material Polyester (PET) Plies no. 2	rfac		FH									
of friction HF Material Polyester (PET) Plies no. 2	ns	Colour	Green									
Plies no. 2			HF									
Plies no. 2	SS	Material	Polyester (PET)									
Weft type Flexible	arca	Plies no.	2									
	ö	Weft type	Flexible									

	Weft type	Flexible	9		
	Material	Fabric	with pol	yurethar	ne (TPU) impregnation
Driving surface	Thickness		mm		in.
Driv	Surface pattern	Fabric			
	Colour	Grey			

TECHNICAL SPECIFICATIONS

Total thickness		2.20 mm	0.09	in.	
Weight		2.20 kg/m^2	0.45	lbs./sq.ft	
Elongation at 1%		12.0 N/mm	69.0	lbs./in.	
Max. admissible pull		24 N/mm	137.0	lbs./in.	
Temperature resistance (1)	min.	-20 °C	-4	°F	
resistance (1)	max.	100 °C	212	°F	
(1) use of the belt with limit va	alues may re	duce its life			

Minimum roller diameter (2)

■ Knife edge no

■ Bending roller 50 mm 2.0 in.

Counter-bending roller 60 mm 2.4 in.

Coefficient of friction on driving surface

Raw steel sheet 0.20 [-]

■ Laminated plastic/wood 0.25 [-]

■ Steel roller 0.20 [-]

■ Rubberized roller 0.30 [-]

Max. production width 1800 mm 71 in.

SUITABLE FOR

Corrugated cardboard

Packaging


Airports

Curve belts

Corrugated cardboard

Steel blankets magnetic elevators

Industrial laundries





FEATURES

Humidity influence					
Suitable to metal detector					
Permanent antistatic dynamically (UNI EN ISO 21179)	yes				
Static conductivity (UNI EN ISO 284)	no				
Conveying on skid bed	yes				
Conveying on rollers	yes				
Conveying on skid bed on top and return	no				
Troughed conveying	yes				
Swan neck conveying	no				
Inclined conveying	yes				
Accumulators belts	no				
Curved conveyor	yes				
Chemical resistances link	6				

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

Last Update: 01-03-2019

Issue: 10-10-2011

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

 $^{^{\}mbox{\scriptsize (2)}}$ The above mentioned values depend on the type of CHIORINO joint recommended



CONVEYOR AND PROCESS BELTS

JOINING DATA SHEET

2T12 U0-U-G10 HS FH NA1135 CODE **TYPE**

· Recommended joining procedure

SKIVED JOINT '4'



Check our general catalogue to get further info on CHIORINO joining methods.

· Skiving instructions

Skiver			Cam/ wedge	Pulley			Top cover					
	mm	mm	diagonal cut	number	T mm	B mm	Thickness adjustment	End stop switch of working plate	T mm	B mm	Thickness adjustment	End stop switch of working plate
B600 A	2,2	50	Diagonal	1,5-1,0	39	0	18,2		39	8	17.2	
B300 SA												

· Guide to the use of adhesives

Pour the I hardener with the R cement (pot-life 2 hours).


Apply a thin layer of above mix on both splices.

Let dry for 5 minutes, then match the belt ends, paying attention to align properly.

Press according to the instructions shown.

To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

· Layout of components



Press settings						
Upper platen temperature	110 °C					
Lower platen temperature	110 °C					
Curing time in press	15 min.					
Driving torque	2,5 bar					

Cooling time: it is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.

Notes

Issue: 03-01-2020 Last Update: 13-06-2022

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.