

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

3M18 U0-V-U30 blue

COMPOSITION					
Conveying surface	Material	Polyurethane (TPU)			
	Thickness	3.00 mm <i>0.118 in.</i>			
	Surface pattern	Smooth			
	Colour	Blue			
	Coefficient of friction	MF			
Textile carcass	Material	Polyester (PET)			
	Plies no.	3			
	Weft type	Rigid			
	Material	Fabric with polyurethane (TPU) impregnation			
Driving surface	Thickness	mm in.			
	Surface pattern	Fabric			
	Colour	Grey			

TECHNICAL SPECIFICATIONS					
Total thickness	6.00 mm	0.24	in.		
Weight	7.00 kg/m^2	1.43	lbs./sq.ft		
Elongation at 1%	18 N/mm	103.0	lbs./in.		
Max. admissible pull	36 N/mm	206.0	lbs./in.		
Temperature resistance (1)	min.	-10 °C	14	°F	
resistance (1)	max.	60 °C	140	°F	
⁽¹⁾ Use of the belt with limit values may reduce its life.					


M:-:(2)		
Minimum radius / diameter (2)		
Knife edge minimum radius	no	
■ Bending roller min. diameter	120 mm	4.72 in.
■ Counter-bending roller min. diameter	300 mm	11.81 in.
(2) The above mentioned values depend on the type of CHIORINO joint recommended.		

Coefficient of friction on driving surface		
Raw steel sheet	0.20 [-]	
Laminated plastic/wood	0.25 [-]	
Steel roller	0.20 [-]	
Rubberized roller	0.30 [-]	

Max. production width 2000 mm 79 in.

SUITABLE FOR

Punchers Recycling



FEATURES	
Humidity influence	no
Suitable to metal detector	
Permanent antistatic dynamically (UNI EN ISO 21179)	
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	
Troughed conveying	no
Swan neck conveying	yes
Inclined conveying	no
Accumulators belts	no
Curved conveyor	no
Chemical resistances link	

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments EC 1935/2004 Regulation and Amendments EC 2023/2006 Regulation and Amendments EU 10/2011, 2023/1442 Regulation and Amendments FDA (Food and Drug Administration)



Last Update: 16-10-2020

NOTES

PRODUCT CODE NA1175

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




CONVEYOR AND PROCESS BELTS

JOINING TECHNICAL DATA SHEET

3M18 U0-V-U30 blue

Recommended joining procedure

SINGLE Z - 80 x 10 mm



Other joining methods can be used:

DOUBLE Z SKIVED JOINT '4'


Check our general catalogue to get further info on CHIORINO joining methods.

Pressing

Heating press P\PL\PLS


Press settings				
Upper platen temperature	175 °C			
Lower platen temperature	175 °C			
Temperature gauge setting	175 °C			
Curing time in press	3 min.			
Pressure	2 bar			
Film	TC370 - PU HP blue film			
Cement				

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
 A periodical inspection of the thermostats is recommended, to make sure they function correctly.

Layout of components



Notes

PRODUCT CODE NA1175

Last Update: 22-06-2023

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.