

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

1M6 U0-S0

COMPOSITION							
Conveying surface	Material	Fabric with silicone impregnation					
	Thickness	mm in.					
	Surface pattern	Fabric					
	Colour	Transparent					
	Coefficient of friction	HF					
Textile carcass	Material	Polyester (PET)					
	Plies no.	1					
	Weft type	Rigid					
	Material	Fabric with polyurethane (TPU) impregnation					
Driving surface	Thickness	mm <i> in.</i>					
	Surface pattern	LdB fabric					
	Colour	White					

TECHNICAL SPECIFICATIONS					
Total thickness	0.60	mm	0.02	in.	
Weight	0.40	kg/m²	0.08	lbs./sq.ft	
Elongation at 1%	6	N/mm	34.0	lbs./in.	
Max. admissible pull	6	N/mm	34.3	lbs./in.	
Temperature resistance (1)	min.	-30	°C	-22	°F
resistance (1)	max.	100	°C	212	°F
⁽¹⁾ Use of the belt with limit values may reduce its life.					

Minimum radius / diameter (2) ■ Knife edge minimum radius no 20 mm 0.79 in. ■ Bending roller min. diameter ■ Counter-bending roller min. diameter 40 mm 1.57 in.

 $^{(2)}$ The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface				
Raw steel sheet	0.20 [-]			
Laminated plastic/wood	0.25 [-]			
Steel roller	0.20 [-]			


Max. production width 2000 mm 79 in.

0.30 [-]

SUITABLE FOR

Rubberized roller

Food industry Packaging



FEATURES		
Humidity influence		
Suitable to metal detector	yes	
Permanent antistatic dynamically (UNI EN ISO 21179)	yes	
Static conductivity (UNI EN ISO 284)	no	
Conveying on skid bed	yes	
Conveying on rollers	yes	
Conveying on skid bed on top and return	no	
Troughed conveying	no	
Swan neck conveying	no	
Inclined conveying	yes	
Accumulators belts	no	
Curved conveyor	no	
Chemical resistances link	10	

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments EC 1935/2004 Regulation and Amendments EC 2023/2006 Regulation and Amendments EU 10/2011, 2023/1442 Regulation and Amendments FDA (Food and Drug Administration)



Last Update: 12-12-2018

NOTES

Ottime caratteristiche di deadesività

PRODUCT CODE NA126

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




CONVEYOR AND PROCESS BELTS

JOINING TECHNICAL DATA SHEET

1M6 U0-S0

Recommended joining procedure

SINGLE Z - 80 x 10 mm



Other joining methods can be used:


Check our general catalogue to get further info on CHIORINO joining methods.

Pressing

P\PL\PLS **Heating press**


Press settings			
Upper platen temperature	160 °C		
Lower platen temperature	160 °C		
Temperature gauge setting	160 °C		
Curing time in press	3 min.		
Pressure	3 bar		
Film	none		
Cement			

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- 3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

· Layout of components



Glossy non-adhesive fabric (ML58)

Notes

Use one layer of AC401 adhesive tape on the conveying side and two foils on the bottom side (TC-10 reinforced foil in contact with the belt and one TC-33 foil between the reinforced foil and the IG-22 silicone pad).

Last Update: 08-01-2018 PRODUCT CODE NA126

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.