

## **CONVEYOR AND PROCESS BELTS**

## **TECHNICAL DATA SHEET**

# 2M12 U0-V7 LG N

COMPOSITION						
Conveying surface	Material	PVC 35 Sh.A (±5)				
	Thickness	0.70 mm <i>0.028 in.</i>				
	Surface pattern	LG				
	Colour	Black				
	Coefficient of friction	HF				
<b>Textile</b> carcass	Material	Polyester (PET)				
	Plies no.	2				
	Weft type	Rigid				
<b>Driving</b> surface	Material	Fabric with polyurethane (TPU) impregnation				
	Thickness	mm in.				
	Surface pattern	LdB fabric				
	Colour	Grey				

TECHNICAL SPECIFICATIONS						
Total thickness	2.70 mm	0.11	in.			
Weight	$2.80 \text{ kg/m}^2$	0.57	lbs./sq.ft			
Elongation at 1%	12 N/mm	69.0	lbs./in.			
Max. admissible pul	24 N/mm	137.0	lbs./in.			
Temperature resistance (1)	min.	-10 °C	14	°F		
resistance (1)	max.	60 °C	140	°F		
(1) Use of the belt with lim	it values may re	duce its life.				

Minimum radius / diameter (2)

■ Knife edge minimum radius no

Bending roller min. diameter
 Counter-bending roller min. diameter
 60 mm
 2.36 in.

 $^{(2)}$  The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface


Raw steel sheet
Laminated plastic/wood
Steel roller
Rubberized roller
0.20 [-]
Rubberized roller
0.30 [-]

Max. production width 2000 mm 79 in.

## SUITABLE FOR

Airports

Materials handling



FEATURES		
Humidity influence		
Suitable to metal detector		
Permanent antistatic dynamically (UNI EN ISO 21179)		
Static conductivity (UNI EN ISO 284)	no	
Conveying on skid bed	yes	
Conveying on rollers	yes	
Conveying on skid bed on top and return		
Troughed conveying	no	
Swan neck conveying	yes	
Inclined conveying	yes	
Accumulators belts	no	
Curved conveyor	no	
Chemical resistances <u>link</u>	4	

Last Update: 10-11-2021

## COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

PRODUCT CODE NA1458

### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




### **CONVEYOR AND PROCESS BELTS**

#### JOINING TECHNICAL DATA SHEET

# 2M12 U0-V7 LG N

## Recommended joining procedure

### SINGLE Z - 80 x 10 mm



#### Other joining methods can be used:

DIAGONAL SINGLE Z DOUBLE Z SKIVED JOINT '2'


Check our general catalogue to get further info on CHIORINO joining methods.

#### Pressing

# Heating press P\PL\PLS


Press settings					
Upper platen temperature	165 °C				
Lower platen temperature	165 °C				
Temperature gauge setting	165 °C				
Curing time in press	3 min.				
Pressure	3 bar				
Film	TC28 - Black PVC film				
Cement					

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
   A periodical inspection of the thermostats is recommended, to make sure they function correctly.

## Layout of components



## Notes

PRODUCT CODE NA1458

Last Update: 28-10-2021

#### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.