

#### **CONVEYOR AND PROCESS BELTS**

#### **TECHNICAL DATA SHEET**

# TYPE 2M5 U0-U0 blue DET

# COMPOSITION

CODE

NA1565

#### Fabric with polyurethane (TPU) impregnation Material Thickness mm Surface Fabric pattern Dark blue Colour Coefficient of friction Material Polyester (PET) Plies no. Weft type Rigid Material Fabric with polyurethane (TPU) impregnation

					-	
iving rface	Thickness		mm	 in.		
Surf	Surface pattern	Fabric				
	Colour	Light b	lue			

#### TECHNICAL SPECIFICATIONS Total thickness 1.00 mm 0.04 in. Weight $1.10 \text{ kg/m}^2$ 0.22 lbs./sq.ft Elongation at 1% 5 N/mm 29.0 lbs./in. Max. admissible pull 57.0 lbs./in. 10 N/mm -30 °C -22 Temperature min. resistance (1) max. 100 ℃ 212 °F <sup>(1)</sup> Use of the belt with limit values may reduce its life.

Minimum radius / diameter (=)		
Knife edge minimum radius	4 mm	0,16 in.
■ Bending roller min. diameter	8 mm	0.31 in.
■ Counter-bending roller min. diameter	16 mm	0.63 in.

<sup>(2)</sup> The above mentioned values depend on the type of CHIORINO joint recommended.

#### Coefficient of friction on driving surface

Raw steel sheet
Laminated plastic/wood
Steel roller
Rubberized roller
0.20 [-]
Rubberized roller
0.30 [-]

Max. production width 2000 mm 79 in.

### SUITABLE FOR

Food: bakery

Food: conveying of dried pasta

Food: chocolate bars

Packaging Paper industry Wood industry





FEATURES		
Humidity influence		
Suitable to metal detector	no	
Permanent antistatic dynamically (UNI EN ISO 21179)	yes	
Static conductivity (UNI EN ISO 284)		
Conveying on skid bed		
Conveying on rollers		
Conveying on skid bed on top and return		
Troughed conveying		
Swan neck conveying		
Inclined conveying		
Accumulators belts		
Curved conveyor		
Chemical resistances <u>link</u>		

#### COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments EC 1935/2004 Regulation and Amendments EC 2023/2006 Regulation and Amendments EU 10/2011, 2023/1442 Regulation and Amendments HACCP (Hazard Analysis and Critical Control Points) FDA (Food and Drug Administration)



NOTES

Issue: 22-01-2020 Last Update: 29-01-2020

#### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



#### **CONVEYOR AND PROCESS BELTS**

#### **JOINING TECHNICAL DATA SHEET**


CODE NA1565

**TYPE** 

# 2M5 U0-U0 HP blue DET

#### Recommended joining procedure

#### SINGLE Z - 80 x 10 mm



#### Other joining methods can be used:

DIAGONAL SINGLE Z DOUBLE Z SKIVED JOINT '1' MICRO Z - 30 x 6 mm


Check our general catalogue to get further info on CHIORINO joining methods.

#### Pressing

## Heating press P\PL\PLS


Press settings					
Upper platen temperature	160 °C				
Lower platen temperature	160 °C				
Temperature gauge setting	160 °C				
Curing time in press	3 min.				
Pressure	3 bar				
Film	TC636 - Film PU Blue DET				
Cement					

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
   A periodical inspection of the thermostats is recommended, to make sure they function correctly.

#### · Layout of components



#### Notes

Seal the belt using the antistatic thread on the covering surface.

Issued: 11-01-2020 Last Update: 11-01-2020

#### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.