

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

EL2-U12 FL/FL N

COMPOSITION						
Conveying surface	Material	Polyurethane (TPU)				
	Thickness	0.60	mm	0.024	in.	
	Surface pattern	FL				
Con	Colour	Black				
	Coefficient of friction	MF				
e S	Material					
Textile carcass	Plies no.					
F 18	Weft type					
Material Polyurethane (TPU)						
Driving surface	Thickness	0.60	mm	0.024	in.	
	Surface pattern	FL				
	Colour	Black				

TECHNICAL SPECIFICATIONS					
Total thickness		1.20	mm	0.05	in.
Weight		1.10	kg/m²	0.22	lbs./sq.ft
Elongation at 8%	2	N/mm	11.0	lbs./in.	
Max. admissible pull		2	N/mm	11.0	lbs./in.
Temperature resistance (1)	min.	-20	°C	-4	°F
resistance (1)	max.	60	°C	140	°F
(1) Use of the belt with limit v	values may re	duce its lif	e.		

Minimum radius / diameter (2)		
Knife edge minimum radius	no	
■ Bending roller min. diameter	10 mm	0.39 in.
Counter-bending roller min. diameter	15 mm	0.59 in.
(2) The above mentioned values depend on the type of CHIORINO joint recommended.		

Coefficient of friction on driving surface

Raw steel sheet	0.40 [-]
Laminated plastic/wood	0.50 [-]
■ Steel roller	0.40 [-]
Rubberized roller	0.60 [-]

Max. production width 2000 mm 79 in.

SUITABLE FOR


Paper industry: cutters Printing and graphic: stacking Printing and graphic: gathering

Printing and graphic: wrapping / binding

Packaging Check weighers

Materials handling: multiple drives

Postal automation Industrial laundries



FEATURES	
Humidity influence	no
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	yes
Troughed conveying	yes
Swan neck conveying	no
Inclined conveying	no
Accumulators belts	no
Curved conveyor	no
Chemical resistances <u>link</u>	5

Last Update: 03-09-2021

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

PRODUCT CODE NA1644

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




CONVEYOR AND PROCESS BELTS

JOINING TECHNICAL DATA SHEET

EL2-U10 FL/FL N

Recommended joining procedure

SINGLE Z - 80 x 10 mm



Other joining methods can be used:

DIAGONAL SINGLE Z MICRO Z - 30 x 6 mm BUTT SPLICE


Check our general catalogue to get further info on CHIORINO joining methods.

Pressing

Heating press P\PL\PLS


Press settings	
Upper platen temperature	155 °C
Lower platen temperature	155 °C
Temperature gauge setting	155 °C
Curing time in press	3 min.
Pressure	2,5 bar
Film	none
Cement	

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
 A periodical inspection of the thermostats is recommended, to make sure they function correctly.

Layout of components



Notes

PRODUCT CODE NA1644 Last Update: 31-03-2021

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.