

TYPE

CONVEYOR AND PROCESS BELTS

NA1717

TECHNICAL DATA SHEET

1DM8 U0-U2 HP W A AM

COMPOSITION

CODE

Material	Polyurethane (TPU) - HP® system			
	0.20	mm	0.008	in.
Surface pattern	Smoot	h		
	Thickness	Thickness 0.20	Thickness 0.20 mm	Thickness 0.20 mm 0.008

White Colour Coefficient of friction

Material Polyester (PET) - HP® system 1 Plies no.

Weft type Double weft rigid Material Fabric polyurethane (TPU) impregn. - HP® system

Thickness in. mm Surface Fabric pattern Light blue Colour

TECHNICAL SPECIFICATIONS

Total thickness		1.35 mm	0.05	in.
Weight		1.40 kg/m ²	0.29	lbs./sq.ft
Elongation at 1%		8 N/mm	46.0	lbs./in.
Max. admissible pull		16 N/mm	91.0	lbs./in.
Temperature resistance (1)	min.	-30 °C	-22	°F
	max.	110 °C	230	°F
(1) Use of the belt with limit	values may re	duce its life.		

Minimum radius / diameter (2)

■ Knife edge minimum radius 4 mm 0,16 in. 0.31 in. ■ Bending roller min. diameter 8 mm ■ Counter-bending roller min. diameter

(2) The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface

0.20 [-] ■ Raw steel sheet ■ Laminated plastic/wood 0.25 [-] Steel roller 0.20 [-] Rubberized roller 0.30 [-]

Max. production width 2100 mm 83 in.

SUITABLE FOR

Food: chocolate cooling tunnel

Food: bakery

Food: biscuits and crackers

Food: dairy

Food: slicing machines Food: seafood processing Pharmaceutics industry

Packaging



FEATURES

Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	no
Chemical resistances <u>link</u>	12

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments EC 1935/2004 Regulation and Amendments EC 2023/2006 Regulation and Amendments EU 10/2011, 2023/1442 Regulation and Amendments HACCP (Hazard Analysis and Critical Control Points) FDA (Food and Drug Administration)





Issue: 10-01-2023 Last Update: 25-09-2023

16 mm

0.63 in

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



CONVEYOR AND PROCESS BELTS

JOINING TECHNICAL DATA SHEET

NA1717 CODE

TYPE

1DM8 U0-U2 HP W A AM

Recommended joining procedure

SINGLE Z - 80 x 10 mm

A = 80 mmB = 10 mm Other joining methods can be used:


Check our general catalogue to get further info on CHIORINO joining methods.

Pressing

P\PL\PLS **Heating press**


Press settings		
Upper platen temperature	150 °C	
Lower platen temperature	150 °C	
Temperature gauge setting	150 °C	
Curing time in press	4 min.	
Pressure	2,5 bar	
Film	TC740 - Film PU HP W AM	
Cement		

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- 3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

· Layout of components



Matt release paper (ML2)

Non-adhesive silicone fabric (TX67)

Notes

Issued: 13-01-2023

Last Update: 11-07-2023

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.