

## CONVEYOR AND PROCESS BELTS

## TECHNICAL DATA SHEET

CODE	NA1741	TYPE	2M6 U0-O2 HY W A
------	--------	------	------------------

### COMPOSITION

Conveying surface	Material	Thermoplastic Polyolefin (TPO)	
	Thickness	0.20 mm	0.008 in.
	Surface pattern	Matt	
	Colour	White	
	Coefficient of friction	LF	
Textile carcass	Material	Polyester (PET)	
	Plies no.	2	
	Weft type	Rigid	
Driving surface	Material	Fabric with polyurethane (TPU) impregnation	
	Thickness	--- mm	--- in.
	Surface pattern	Fabric	
	Colour	White	

### TECHNICAL SPECIFICATIONS

Total thickness	1.40 mm	0.06 in.
Weight	1.50 kg/m <sup>2</sup>	0.31 lbs./sq.ft
Elongation at 1%	6 N/mm	34.0 lbs./in.
Max. admissible pull	12 N/mm	69.0 lbs./in.
Temperature resistance <sup>(1)</sup>	min.	-40 °C -40 °F
	max.	80 °C 176 °F

<sup>(1)</sup> Use of the belt with limit values may reduce its life.

Minimum radius / diameter <sup>(2)</sup>		
■ Knife edge minimum radius	4 mm	0,16 in.
■ Bending roller min. diameter	20 mm	0.79 in.
■ Counter-bending roller min. diameter	25 mm	0.98 in.


<sup>(2)</sup> The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface	
■ Raw steel sheet	0.30 [-]
■ Laminated plastic/wood	0.35 [-]
■ Steel roller	0.30 [-]
■ Rubberized roller	0.40 [-]

Max. production width	1600 mm	63 in.
-----------------------	---------	--------

### SUITABLE FOR

- Food: confectionery
- Food: chocolate bars
- Food: chocolate cooling tunnel
- Food: bakery
- Food: dairy
- Food: meat and fish processing
- Food: poultry
- Food: seafood processing



**HYPERCLEAN**

### FEATURES

Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	no
Accumulators belts	no
Curved conveyor	no
Chemical resistances <a href="#">link</a>	12

### COMPLIANCES

- REACH EC 1907/2006 Regulation and Amendments
- EC 1935/2004 Regulation and Amendments
- EC 2023/2006 Regulation and Amendments
- EU 10/2011, 2023/1442 Regulation and Amendments
- FDA (Food and Drug Administration)



### NOTES

- Frayless** - Edge fray total resistance
- Maximum production width 1600 mm. Requests for production in wider widths must be authorized by Chiorino Technical Management

Issue: 06-02-2024


Last Update: 27-03-2024

### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

CODE **NA1741** TYPE **2M6 U0-O2 HY W A**

Recommended joining procedure **SINGLE Z - 80 x 10 mm**



A = 80 mm  
B = 10 mm

Other joining methods can be used:  
DIAGONAL SINGLE Z

Check our general catalogue to get further info on CHIORINO joining methods.

• Pressing

Heating press **P \ PL \ PLS**

Press settings	
Upper platen temperature	125 °C
Lower platen temperature	100 °C
Temperature gauge setting	100 °C
Curing time in press	3 min.
Pressure	2 bar
Film	none
Cement	---


1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.

3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

• Layout of components



• Notes

Issued: 02-02-2024

Last Update: 15-02-2024

**DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.