

### **CONVEYOR AND PROCESS BELTS**

### **TECHNICAL DATA SHEET**

# ChioLink G40 HS GP blue

COMPOSITION				
Conveying surface	Material	Synthetic elastomer (NBR)		
	Thickness	4.50 mm <i>0.177 in.</i>		
	Surface pattern	GP		
	Colour	Blue		
	Coefficient of friction	MF		
<b>Textile</b> carcass	Material			
	Plies no.			
	Weft type			
<b>Driving</b> surface	Material	Mesh, polyester		
	Thickness	2.50 mm <i>0.098 in.</i>		
	Surface pattern			
	Colour			

	TECHNICAL SPE	CIFICATIO	NS			
Total thickness			7.00	mm	0.28	in.
Weight			8.00	kg/m²	1.63	lbs./sq.ft
Elongation at 1%			13	N/mm	74.0	lbs./in.
Max. admissible pull			13	N/mm	74.0	lbs./in.
Te	emperature sistance <sup>(1)</sup>	min.	-20	°C	-4	°F
re		max.	100	°C	212	°F
<sup>(1)</sup> Use of the belt with limit values may reduce its life.						


Minimum radius / diameter (2)		
Knife edge minimum radius	no	
■ Bending roller min. diameter	80 mm	3.15 in.
■ Counter-bending roller min. diameter	100 mm	3.94 in.
(2) The above mentioned values depend on the type of (	CHIORINO joint r	ecommende

12) The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface				
Raw steel sheet	0.30 [-]			
Laminated plastic/wood	0.35 [-]			
Steel roller	0.25 [-]			
Rubberized roller	0.35 [-]			
Max. production width	1000 mm	39 in.		

## SUITABLE FOR

Corrugated cardboard Wood industry



# **CHIOLINK**

Last Update: 24-04-2024

FEATURES	
Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	no
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	yes
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	no
Chemical resistances <u>link</u>	8

#### COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

## NOTES

Fast splicing without presses, fasteners or glues

PRODUCT CODE NA1797

#### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.