CHIORINO 1906

CONVEYOR AND PROCESS BELTS **TECHNICAL DATA SHEET**

2M12 U0-V8 RT

COMPOSITION

Conveying surface	Material	PVC 45 Sh.A (±5)		
	Thickness	0.80 mm	*0.031*	*in.*
	Surface pattern	RT		
	Colour	Green		
	Coefficient of friction	HF		
Textile carcass	Material	Polyester (PET)		
	Plies no.	2		
	Weft type	Rigid		
Driving surface	Material	Fabric with polyurethane (TPU) impregnation		
	Thickness	--- mm	---	*in.*
	Surface pattern	LdB fabric		
	Colour	Grey		



TECHNICAL SPECIFICATIONS

Total thickness		2.30 mm	*0.09*	*in.*
Weight		2.40 kg/m²	*0.49*	*lbs./sq.ft*
Elongation at 1%		12 N/mm	*69.0*	*lbs./in.*
Max. admissible pull		24 N/mm	*137.0*	*lbs./in.*
Temperature resistance [1]	min.	-10 °C	*14*	*°F*
	max.	60 °C	*140*	*°F*

[1] Use of the belt with limit values may reduce its life.

Minimum radius / diameter [2]

Knife edge minimum radius	no		
Bending roller min. diameter	40 mm	*1.57*	*in.*
Counter-bending roller min. diameter	60 mm	*2.36*	*in.*

[2] The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface

Raw steel sheet	0.20 [-]
Laminated plastic/wood	0.25 [-]
Steel roller	0.20 [-]
Rubberized roller	0.30 [-]

Max. production width	2000 mm	*79*	*in.*

SUITABLE FOR

Textile: nonwoven
Wood industry
Printing and graphic
Packaging
Materials handling
Tanning industry

FEATURES

Humidity influence	no
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	yes
Inclined conveying	yes
Accumulators belts	no
Curved conveyor	no
Chemical resistances link	4

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

PRODUCT CODE NA33 Last Update: 23-06-2016

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

2M12 U0-V8 RT

Recommended joining procedure SINGLE Z - 80 x 10 mm



A = 80 mm
B = 10 mm

Other joining methods can be used:

DIAGONAL SINGLE Z
DOUBLE Z
SKIVED JOINT '2'

Check our general catalogue to get further info on CHIORINO joining methods.

• Pressing

Heating press **P \ PL \ PLS**

Press settings	
Upper platen temperature	170 °C
Lower platen temperature	170 °C
Temperature gauge setting	170 °C
Curing time in press	4 min.
Pressure	3 bar
Film	TC29 - Green PVC film
Cement	---

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.
3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
   A periodical inspection of the thermostats is recommended, to make sure they function correctly.

• Layout of components



Upper heated platen
Upper synthetic plate
RT silicone pad (IG12)
Film
Belt

Lower synthetic plate
Lower heated platen

• Notes

PRODUCT CODE NA33 Last Update: 30-01-2014

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.