



## CONVEYOR AND PROCESS BELTS

## TECHNICAL DATA SHEET

| CODE  | NA37                    | TYPE  | 2M20 U0-V25 RT  |
|---|-------------------------|---|---|
| <b>COMPOSITION</b>  |                         |   |   |
| Conveying surface   | Material                | PVC 65 Sh.A (±5)                            |   |
|   | Thickness               | 2.50 mm                                     | 0.098 in.   |
|   | Surface pattern         | RT  |   |
|   | Colour                  | Green                                       |   |
|   | Coefficient of friction | MF  |   |
| Textile carcass   | Material                | Polyester (PET)                             |   |
|   | Plies no.               | 2   |   |
|   | Weft type               | Rigid                                       |   |
| Driving surface   | Material                | Fabric with polyurethane (TPU) impregnation |   |
|   | Thickness               | ---   | mm --- in.  |
|   | Surface pattern         | LdB fabric                                  |   |
|   | Colour                  | Grey  |   |
| <b>TECHNICAL SPECIFICATIONS</b>   |                         |   |   |
| Total thickness   | 5.00 mm                 | 0.20 in.                                    |   |
| Weight  | 5.70 kg/m <sup>2</sup>  | 1.16 lbs./sq.ft                             |   |
| Elongation at 1%  | 20 N/mm                 | 114.0 lbs./in.                              |   |
| Max. admissible pull  | 40 N/mm                 | 228.0 lbs./in.                              |   |
| Temperature resistance <sup>(1)</sup>   | min.                    | -10 °C                                      | 14 °F   |
|   | max.                    | 60 °C                                       | 140 °F  |
| <sup>(1)</sup> Use of the belt with limit values may reduce its life.                       |                         |   |   |
| Minimum radius / diameter <sup>(2)</sup>  |                         |   |   |
| ■ Knife edge minimum radius   | no                      |   |   |
| ■ Bending roller min. diameter  | 100 mm                  | 3.94 in.                                    |   |
| ■ Counter-bending roller min. diameter  | 150 mm                  | 5.91 in.                                    |   |
| <sup>(2)</sup> The above mentioned values depend on the type of CHIORINO joint recommended. |                         |   |   |
| Coefficient of friction on driving surface  |                         |   |   |
| ■ Raw steel sheet   | 0.20 [-]                |   |   |
| ■ Laminated plastic/wood  | 0.25 [-]                |   |   |
| ■ Steel roller  | 0.20 [-]                |   |   |
| ■ Rubberized roller   | 0.30 [-]                |   |   |
| Max. production width   | 2000 mm                 | 79 in.                                      |   |
| <b>SUITABLE FOR</b>   |                         |   |   |
| Ceramic industry  |                         |   |   |
| Marble and granite industry   |                         |   |   |
| Steel blankets magnetic elevators   |                         |   |   |
| <b>FEATURES</b>   |                         |   |   |
| Humidity influence  | no                      |   |   |
| Suitable to metal detector  | yes                     |   |   |
| Permanent antistatic dynamically (UNI EN ISO 21179)   | no                      |   |   |
| Static conductivity (UNI EN ISO 284)  | no                      |   |   |
| Conveying on skid bed   | yes                     |   |   |
| Conveying on rollers  | yes                     |   |   |
| Conveying on skid bed on top and return   | no                      |   |   |
| Troughed conveying  | no                      |   |   |
| Swan neck conveying   | no                      |   |   |
| Inclined conveying  | yes                     |   |   |
| Accumulators belts  | no                      |   |   |
| Curved conveyor   | no                      |   |   |
| Chemical resistances <a href="#">link</a>   | 3                       |   |   |
| <b>COMPLIANCES</b>  |                         |   |   |
| REACH EC 1907/2006 Regulation and Amendments  |                         |   |  |
| EC 1935/2004 Regulation and Amendments  |                         |   |   |
| EC 2023/2006 Regulation and Amendments  |                         |   |   |
| EU 10/2011, 2023/1442 Regulation and Amendments   |                         |   |   |
| FDA (Food and Drug Administration)  |                         |   |   |
| <b>NOTES</b>  |                         |   |   |



Issue: 24-07-2009

Last Update: 12-12-2018

### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

CODE **NA37** TYPE **2M20 U0-V25 RT**

Recommended joining procedure **SINGLE Z - 80 x 10 mm**



Other joining methods can be used:  
STEP


Check our general catalogue to get further info on CHIORINO joining methods.

• Pressing

Heating press **P \ PL \ PLS**


| Press settings            |                       |
|---------------------------|-----------------------|
| Upper platen temperature  | 175 °C                |
| Lower platen temperature  | 175 °C                |
| Temperature gauge setting | 175 °C                |
| Curing time in press      | 3 min.                |
| Pressure                  | 3 bar                 |
| Film                      | TC29 - Green PVC film |
| Cement                    | ---                   |

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.  
3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

• Layout of components



• Notes

After a first pressing to make the belt endless, proceed with a second pressing operation using the RT impression pad with platens temperature 150 centigrades.

Issued: 08-11-2005

Last Update: 30-01-2014

**DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.