

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

2T12 V10-V12 AGR

COMPOSITION						
Conveying surface	Material	PVC 60 Sh.A (±5)				
	Thickness	1.20 mm <i>0.047 in.</i>				
	Surface pattern	Smooth				
	Colour	Green				
	Coefficient of friction	MF				
Textile carcass	Material	Polyester (PET)				
	Plies no.	2				
	Weft type	Flexible				
Driving surface	Material	PVC 60 Sh.A (±5)				
	Thickness	1.00 mm <i>0.039 in.</i>				
	Surface pattern	PN				
	Colour	Green				

TECHNICAL SPECIFICATIONS						
Total thickness		4.00	mm	0.16	in.	
Weight		4.60	kg/m²	0.94	lbs./sq.ft	
Elongation at 1%		12	N/mm	69.0	lbs./in.	
Max. admissible pull		24	N/mm	137.0	lbs./in.	
Temperature resistance (1)	min.	-15	°C	5	°F	
resistance (1)	max.	60	°C	140	°F	
⁽¹⁾ Use of the belt with limit values may reduce its life.						
Minimum radius / diameter (2)						
Knife edge minimu	m radius			no		

Minimum radius / diameter * /				
Knife edge minimum radius	no			
■ Bending roller min. diameter	80 mm	3.15 in.		
■ Counter-bending roller min. diameter	120 mm	4.72 in.		
$^{(2)}$ The above mentioned values depend on the type of CHIORINO joint recommended.				

Coefficient of friction on driving surface

■ Raw steel sheet ■ Laminated plastic/wood ■ Steel roller 0.40 [-] Rubberized roller 0.60 [-] Max. production width 2000 mm 79 in.

SUITABLE FOR

Fruits and vegetables



FEATURES		
Humidity influence		
Suitable to metal detector		
Permanent antistatic dynamically (UNI EN ISO 21179)		
Static conductivity (UNI EN ISO 284)		
Conveying on skid bed		
Conveying on rollers		
Conveying on skid bed on top and return		
Troughed conveying		
Swan neck conveying		
Inclined conveying		
Accumulators belts		
Curved conveyor		
Chemical resistances <u>link</u>		

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

Better resistance to low temperatures than the standard PVC

PRODUCT CODE NA814 Last Update: 30-08-2016

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




CONVEYOR AND PROCESS BELTS

JOINING TECHNICAL DATA SHEET

2T12 V10-V12 AGR

Recommended joining procedure

SINGLE Z - 80 x 10 mm



Other joining methods can be used:

DOUBLE Z SKIVED JOINT '1' STEP


Check our general catalogue to get further info on CHIORINO joining methods.

Pressing

Heating press P\PL\PLS


Press settings				
Upper platen temperature	170 °C			
Lower platen temperature	170 °C			
Temperature gauge setting	170 °C			
Curing time in press	3 min.			
Pressure	3 bar			
Film	TC384 - Apple green PVC film			
Cement				

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
 A periodical inspection of the thermostats is recommended, to make sure they function correctly.

Layout of components



Notes

PRODUCT CODE NA814

Last Update: 30-01-2014

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.