

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

1M12 U0-V5 N

COMPOSITION						
Conveying surface	Material	PVC 70 Sh.A (±5)				
	Thickness	0.50 mm <i>0.020 in.</i>				
	Surface pattern	Smooth				
	Colour	Black				
	Coefficient of friction	LF				
Textile carcass	Material	Polyester (PET)				
	Plies no.	1				
	Weft type	Rigid				
	Material	Fabric with polyurethane (TPU) impregnation				
Driving surface	Thickness	mm <i> in.</i>				
	Surface pattern	LdB fabric				
	Colour	Grey				

TECHNICAL SPECIFICATIONS					
Total thickness	1.80	mm	0.07	in.	
Weight	2.00	kg/m²	0.41	lbs./sq.ft	
Elongation at 1%	8	N/mm	46.0	lbs./in.	
Max. admissible pull	12	N/mm	68.5	lbs./in.	
Temperature resistance (1)	min.	-10	°C	14	°F
resistance (1)	max.	60	°C	140	°F
(1) Use of the belt with limit v	alues may re	duce its life	е.		

Minimum radius / diameter (2)		
Knife edge minimum radius	no	
■ Bending roller min. diameter	30 mm	1.18 in.
■ Counter-bending roller min. diameter	50 mm	1.97 in.
$^{\left(2\right) }$ The above mentioned values depend on the type of CHIORINO joint recommended.		

Coefficient of friction on driving surface

Raw steel sheet	0.20 [-]	
Laminated plastic/wood	0.25 [-]	
■ Steel roller	0.20 [-]	
Rubberized roller	0.30 [-]	
Max. production width	2000 mm	79 in.

SUITABLE FOR

Supermarkets check-outs Materials handling



FEATURES	
Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	no
Accumulators belts	no
Curved conveyor	no
Chemical resistances link	2

Last Update: 20-12-2018

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments Flame Retardant UNI EN ISO 340 Flame Retardant UL94HB Horizontal Burning

NOTES

PRODUCT CODE NA904

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




CONVEYOR AND PROCESS BELTS

JOINING TECHNICAL DATA SHEET

1M12 U0-V5 N

Recommended joining procedure

SINGLE Z - 80 x 10 mm



Other joining methods can be used:

DIAGONAL SINGLE Z


Check our general catalogue to get further info on CHIORINO joining methods.

Pressing

P\PL\PLS **Heating press**


Press settings	
Upper platen temperature	170 °C
Lower platen temperature	170 °C
Temperature gauge setting	170 °C
Curing time in press	3 min.
Pressure	3 bar
Film	TC28 - Black PVC film
Cement	

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- 3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

· Layout of components



Notes

Last Update: 30-01-2014 PRODUCT CODE NA904

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.