

CODE TX170

TYPE

SG0-E nc


**STRUCTURE**

**External covering**

|                   |                          |
|-------------------|--------------------------|
| Material          | Synthetic elastomer      |
| Surface pattern   | Porous and grinded       |
| Special execution | Foam synthetic elastomer |
| Colour            | Hazelnut                 |
| Hardness          | 40 ±5 Sh.A               |

**Textile carcass**

|          |                 |
|----------|-----------------|
| Material | Polyester (PET) |
|----------|-----------------|



**TECHNICAL SPECIFICATIONS**

|                            |                          |                 |
|----------------------------|--------------------------|-----------------|
| Total thickness            | 2.7 mm                   | 0.11 in.        |
| Weight                     | 2.2 kg/m <sup>2</sup>    | 0.45 lbs./sq.ft |
| Tensile strength           | 60 N/mm                  | 343 lbs./in.    |
| Temperature resistance (1) | min -10 °C<br>max 120 °C | 14 °F<br>248 °F |

(1) Use of the roller covering with limit values may reduce its life

**ROLL SIZES**

|           |       |          |
|-----------|-------|----------|
| Length    | 115 m | 4528 in. |
| Width (2) | 50 mm | 2 in.    |
|           | 70 mm | 3 in.    |

(2) Other widths upon request

**SUITABLE FOR**

Textile: weaving

**ADHESIVES**

- To glue the covering to the roller it is recommendable to use the single-component adhesive TEXCOL CHIORINO

**FEATURES**

- Good shock-absorption properties

**COMPLIANCES**

REACH Regulation EC 1907/2006 and amendments

**NOTES**

Issue: 10-10-2006

Last Update: 25-02-2021

**DISCLAIMER**

The information contained in this document describes the features of the Chiorino product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the Chiorino product. Chiorino cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.